

POLYKEN® 942-AS & 955 EN

Product Information

Product description: The Polyken® 942-AS /955 EN system is an asymmetric co-extruded multilayer coating system designed for the corrosion protection of new construction cross country pipelines / plant piping / pipeline coating rehabilitation operating in highly corrosive environments and exposed to high mechanical stresses that may be present particularly on large diameter pipes. The system consists of 1027 liquid adhesive, 942 asymmetric three ply anti-corrosion inner layer and 955 EN mechanical outer layer and is fully tested to the EN12068 Class C50 and ISO-21809-11.

The asymmetric three ply adhesive system produces a strong cohesive bond to the primed steel surface, at the spiral overlap and to the mechanical outer layer. The tough mechanical properties of the outer layer provide protection to the pipes during handling and installation. The coating system is compatible with the cathodic protection system.

Features:

- Thick adhesive layer towards the primed steel surface.
- Fully amalgamating overlapping areas
- Impermeable to oxygen and moisture.
- Resistant to soil stress.
- Uniform coating thickness.
- Low cathodic protection-current requirements.
- Compatible with all pipe diameters and generic plant coating systems.

Benefits:

- Forming a sleeve-type coating.
- Proven long-term in-ground performance.
- Superior in-ground performance.
- Plant coating quality in-situ application.
- Saving cost over the life of the pipeline.
- Minimizes inventory, thus saving money.

Product selection guide

Max.exposure temperature	85°C
Maximum operating temperature	65°C
Compatible line coatings	PE, FBE, PP, CTE, Tape,
Recommended pipe preparation	SA 21/2 or ST-3
Recommended primer	1027
Performance (Based On SA 2 ½)	EN12068 class C50

Product construction

	942-AS-30	955 22 EN	955 28 EN
Tape thickness	30 mils	22 mils	28 mils
Carrier Thickness	11 mils	14 mils	14 mils
Butyl adhesive inside	16mils	8 mils	14 mils
Butyl adhesive Outside	3 mils	-	-
Color	Black/Grey	Black	Black

Ordering information

Polyken® 942-AS and 955 EN Tape Coatings are available in roll form.

Example **942-AS 30-100MMX30M -C41**

942-AS	Product type	Standard Ordering options
30	Product thickness in mils	30 (0.75 mm)
100	Tape width in mm	50 mm , 100 mm, 150 mm
30	Tape roll length in meter	15 m ,30 m, 60m*
C41	Tape inner core diameter in mm	41 mm, 76 mm*

955-22 EN BLK 100MMX30M C41

955 EN	Product type	Standard Ordering options
22	Product thickness in mils	22 (0,55 mm), 28 (0.70 mm)
BLK	Tape backing color	Black (BLK)
100	Tape width in mm	50 mm, 100 mm, 150 mm
30	Tape roll length in meter	15 m ,30 m, 60m*
C41	Core inside diameter in mm	41 mm , 76 mm*

* Only for 150 mm wide rolls

For other ordering options please contact your Seal For Life representative.

Product properties

Property	Method	Typical values			Units
		942 AS	955-22 EN	955-28 EN	
Tensile strength	EN12068	> 35 > 6	> 30 > 5.2	> 30 > 5.2	pli N/mm
Elongation	EN12068	> 500	> 400	> 400	%
System properties					
two layers 942-AS-30 and two layers 955-22 EN					
Shear resistance	EN12068, @ 50°C		0.09		N/mm ²
Peel adhesion	EN12068, @ 10 mm/min @ 23°C		1.6		N/mm
Peel adhesion inner to inner	EN12068, @ 100 mm/min @ 23°C		2.8		N/mm
Peel adhesion outer to inner	EN12068, @ 100 mm/min @ 23°C		2.6		N/mm
Peel adhesion outer to outer	EN12068, @ 100 mm/min @ 23°C		0.6		N/mm
Cathodic disbondment	EN12068, @ 23°C		2		mm radius
Dielectric strength (942-AS)	ASTM D149		31		kV
Impact resistance	EN12068, class C		> 15		J
Indentation resistance	EN12068, @ 50°C		1.2		mm remaining thickness
Specific Electrical insulation resistance	EN12068		> 10 ⁹		Ωm ²
Peel adhesion After 28 days hot water immersion	ISO 21809-3, @ 10 mm/min @ 23°C		1.2		N/mm

Note: The typical values in this data sheet are based on lab prepared samples. Values shown are not to be interpreted as product specifications. All tests are done at 23°C unless specified otherwise. All tests were conducted on SA 2 ½ prepared samples.

Equation for Pipe Coating Requirements

Squares** of coating required	$\frac{(\text{width of coating in inches}) \times (\text{area of pipe in square feet})^*}{(\text{width of coating in inches} - \text{overlap in inches}) \times 100}$
	* Area of pipe in ft ² = (diameter in inches / 12) x 3.1416 x length in feet ** One Square = one hundred square feet = 9.29 square meters
Square meters of coating required	$\frac{(\text{width of coating in mm}) \times (\text{area of pipe in square meter})^*}{(\text{width of coating in mm} - \text{overlap in mm})}$
	* Area of pipe in m ² = (diameter in mm / 1000) x 3.1416 x length in meter
Squares** per roll	$\frac{(\text{width of roll in inches})}{(12)} \times \frac{(\text{length of roll in feet})}{(100)}$
Square meters Per roll	$\frac{(\text{width of roll in mm})}{(1000)} \times (\text{length of roll in m})$
Rolls Required	$\frac{(\text{squares of coating required})}{(\text{squares per roll})}$
Rolls Required	$\frac{(\text{square meters of coating required})}{(\text{square meters per roll})}$

Application instruction: Job preparation	
Tools, equipment and auxiliaries	Temperature gauge, DFT/WFT gauge Primer application equipment/agitator, Tape application equipment, Coating "hot box"
Additional coating materials	939 mastic (for filling voids / transition areas / weld seams))
High humidity	Polyken® 942-AS/955 can be applied in a humid atmosphere. The substrate should be free from condensing water which can be reached by keeping the temperature at least 5°F (3°C) above dew point.
Work area and substrate	The substrate surface should be dry, clean and protected against negative weather influences.
Product conditions	The Polyken® 942-AS/955 shall be stored and/or transported in a dry, ventilated location. Storage temperature shall be a minimum of 15°C and a maximum of 50°C. The minimum primer and roll body temperature for application will be 15°C.

Application instruction: Surface preparation	
General	The area to be coated has to be clean, dry, and free from oil, grease and dust. All contamination including mill-scale has to be removed.
Degreasing	Degrease surfaces with Toluene or Heptane and e.g. a lint-free cloth.
Preventing condensation of water	Prior to and during the application, the temperature of the substrate(s) must be at least 5°F (3°C) above the dew point.
Substrate temperature	Temperature of the substrate should preferably be between 10°C and 50°C.

Application instruction: Brief version	
Step 1	Clean substrate to SA 21/2 or ST-3
Step 2	Uniform primer application achieving 2 to 3 mil WFT. Primer should be "dry to touch" before application of inner layer.
Step 3	If required, apply weld seam coating (939)
Step 4	Start application a minimum of 4" beyond cutback edge.

Step 4	Spirally apply the 942-AS inner layer (anti corrosion) with the black adhesive side towards the primed steel and with a 1% to 2% neckdown and no less than a 50% overlap
Step 6	Spirally apply the 955 EN outer layer (mechanical Protection) with a 1% to 2% neckdown and no less than a 50% overlap.
Step 7	Perform holiday detection per EN12068 or ISO-21809-3

Pipe handling and commissioning	
Exposure to loads	Objects coated with Polyken® 942-AS/955 should not be exposed to loads e.g. from supports- or lifting equipment.
Backfill	Backfill is possible immediately after completion of the coating application. Consult application guidelines for specific instructions. Backfill should be clean and not contain any foreign items that can cause damage to the coating system.

Tape handling and storage	
Handling	Handle with care. Keep boxes upright.
Storage	Store indoor, clean and dry, away from direct sunlight in a cool place below +40°C. In these conditions the 942-AS and 955 EN tape have 5 years shelf life from Day of Manufacturing (DOM).

Information	
Documentation	Extensive information is available on our website. Application instructions and other documentation can be obtained by contacting our offices, from our local distributor or by sending an email to info@sealforlife.com
Certified staff	Application of the described coating system should be carried out by certified personnel.

* For further detailed information, please view the corresponding Application Guideline *

Supplied by:

LORDCO
AN ANODE ENGINEERING COMPANY

PH: 04 939 3944
sales@lordco.co.nz

	SEALFORLIFE	Seal For Life Industries - Stopaq B.V. Stadskanaal, the Netherlands Tel: +31 599 696 170	Seal For Life Industries BV Westerlo, Belgium Tel: +32 14 722 500	Seal For Life Industries US LLC San Diego, USA Tel: +1 858 633 9785	Seal For Life Industries Mexico S de R.L. de C.V. Tijuana, Mexico US Tel: +1 858 633 9785 MX Tel: +52 664 647 4300	Seal For Life India Private Ltd. Baroda, India Tel: +91 2667 264 721
	Industries					

Further information is available on our website www.sealforlife.com, or by sending an inquiry to info@sealforlife.com

DISCLAIMER: Seal For Life Industries warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the technical data sheet when used in compliance with Seal For Life Industries' written instructions. Because many installation factors are beyond the control of Seal For Life Industries, the user shall determine the suitability of the products for the intended uses and assume all risks and liabilities in connection herewith. Seal For Life's liability is stated in its General Terms and Conditions of Sale. Seal For Life Industries makes no other warranty either express or implied. All information contained in this document is to be used as a guide and is subject to change without notice. This technical data sheet supersedes all previous data sheets on this product.